



Hebei Gezi Filtration Industry Co., Ltd

Composition		PET/PET scrim
Thickness (mm)		1.8
Air permeability (L/m ² /s)		200-350
Tensile strength (N/5×20cm)	Warp	1100
	Weft	1300
Tensile elongation (%)	Warp	< 35
	Weft	< 40
Broken strength (N/m ²)		450
Continuous working Tem. (°C)		130
Short time working Tem.(°C)		150
Anti-acid		Fair
Anti-alkali		Fair
Anti-abrasion		Excellent
The stability of water solution		Fair
Finishing treatment		Singeing, calendaring, heating (Mirror treatment)

Copyright ©1997-2014 Hebei Gezi Filtration Industry Co.,Ltd

www.screenmesh-cloth.com

sales@screenmesh-cloth.com bob.yimesh@gmail.com

Call us: +86 311 80815968