



Hebei Gezi Filtration Industry Co., Ltd

Compositions		PP/PP ordinary scrim	
Weight (g/ m2)		500	550
Thickness (mm)		2.1	2.3
Air permeability (L/m2/s)		12.6	10.8
Tensile strength (N/5 20cm)	wrap	>960	>1200
	weft	>1060	>1500
Tensile Elongation(%)	wrap	<35	<35
	weft	<55	<55
Broken strength (Mpa/min)		2.15	2.10
Continuous working temperature(°C)		88	88
Short time Working temperature(°C)		110	110
Anti-acid		Excellent	Excellent
Anti-alkali		Excellent	
Anti-abrasion		Excellent	
The stability of water solution		Excellent	
Finishing treatment		High temperature hot pressing,Singeing	

Copyright ©1997-2014 Hebei Gezi Filtration Industry Co.,Ltd

www.screenmesh-cloth.com

sales@screenmesh-cloth.com bob.yimesh@gmail.com

Call us: +86 311 80815968