



Hebei Gezi Filtration Industry Co., Ltd

| 滤料名称 Filter | | PPS针刺毡 PPS needle felt | 诺美塔斯针刺毡 Metamax needle felt | P84针刺毡 P84 needle felt | 氟耐斯针刺毡 FNS needle felt | 玻璃纤维针刺毡 Glass fiber needle felt |
|---|----------------|---|---|--|--|--|
| 性能指标 Performance parameter | | | | | | |
| 克重Weight(g/㎡) | | 500 | 500 | 500 | 800 | 800 |
| 材质Material | | PPS短纤PPS staple fiber | 诺美塔斯 Metamax fiber | P84/P84 | P84/玻纤/PTFE P84/Glass fiber/PTFE | 玻纤Glass fiber |
| 厚度Thickness (mm) | | 1.80 | 2.00 | 2.00 | 2.50 | 2.40 |
| 透气率 Air permeability (L/㎡/s) | | 200-300 | 200-400 | 200-300 | 200-300 | 200-300 |
| 断裂强度 Tensile strength (N/5*20cm) | 径向Warp | 1250 | 1300 | 1100 | 3260 | 1800 |
| | 纬向Weft | 1350 | 1460 | 1200 | 3300 | 1800 |
| 断裂伸长度 Tensile elongation (%) | 径向Warp | 40 | 50 | 25 | 10 | 10 |
| | 纬向Weft | 60 | 55 | 35 | 15 | 10 |
| 工作温度 Temperature (°C) | 连续 Continue | 190 | 204 | 260 | 260 | 240 |
| | 瞬间 Instant | 220 | 240 | 280 | 300 | 260 |
| 后处理方式 Finishing treatment | | 热定型、烧光、 轧光Heating, Singeing, Calendering | 热定型、烧光、 轧光Heating, Singeing, Calendering | PTFE浸渍、定型 PTFE dip forming process | PTFE浸渍、定型 PTFE dip forming process | PTFE浸渍、定型 PTFE dip forming process |

Copyright ©1997-2014 Hebei Gezi Filtration Industry Co.,Ltd

www.screenmesh-cloth.com

sales@screenmesh-cloth.com bob.yimesh@gmail.com

Call us: +86 311 80815968