



## Hebei Gezi Filtration Industry Co., Ltd

Compositions	polyester+ easily dedusting treating	
Weight (g/m <sup>2</sup> )	500	
Thickness (mm)	1.80	
Air permeability (m <sup>3</sup> /m <sup>2</sup> /min)	14-25	
Tensile strength (N/5×20cm)	warp	1300
	weft	1650
Tensile elongation (%)	warp	<30
	weft	<45
Broken strength (Mpa/min)	2.75	
Continuous working temperature (°C)	130	
Short time Working temperature(°C)	150	
Anti-acid	Fair	
Anti-alkali	Fair	
Anti-abrasion	Excellent	
The stability of water solution	Fair	
Finishing treatment	High temperature hot pressing, Singeing	

Copyright ©1997-2014 Hebei Gezi Filtration Industry Co.,Ltd

[www.screenmesh-cloth.com](http://www.screenmesh-cloth.com)

[sales@screenmesh-cloth.com](mailto:sales@screenmesh-cloth.com) [bob.yimesh@gmail.com](mailto:bob.yimesh@gmail.com)

Call us: +86 311 80815968