



Hebei Gezi Filtration Industry Co., Ltd

Composition	PET/anti-static scrim	
Weight (g/m ²)	500	
Thickness (mm)	1.80	
Air permeability (L/m ² /s)	200-350	
Tensile strength (N/5×20cm)	Warp	1000
	Weft	1250
Tensile elongation (%)	Warp	<35
	Weft	<55
Broken strength (Mpa/min)	2.40	
Working temperature(°C)	130	
Short time working temperature (°C)	150	
Anti-acid	Fair	
Anti-alkali	Fair	
Anti-abrasion	Excellent	
The stability of water solution	Fair	
Finishing treatment	Singeing, calendaring	

Copyright ©1997-2014 Hebei Gezi Filtration Industry Co.,Ltd

www.screenmesh-cloth.com

sales@screenmesh-cloth.com bob.yimesh@gmail.com

Call us: +86 311 80815968