



Hebei Gezi Filtration Industry Co., Ltd

| | | |
|------------------------------------|--|------|
| Compositions | PPS stable fiber | |
| Weight (g/ m2) | 500 | |
| Thickness (mm) | 1.8 | |
| Air permeability (L/m2/s) | 200-300 | |
| Tensile strength (N/5 20cm) | wrap | 1250 |
| | weft | 1350 |
| Tensile Elongation(%) | wrap | 30 |
| | weft | 30 |
| Broken strength (Mpa/min) | 2.6 | |
| Continuous working temperature(°C) | ≤190 | |
| Short time Working temperature(°C) | 230 | |
| Anti-acid | Excellent | |
| Anti-alkali | Excellent | |
| Anti-abrasion | Excellent | |
| The stability of water solution | Excellent | |
| Finishing treatment | High temperature hot pressing,Singeing | |

Copyright ©1997-2014 Hebei Gezi Filtration Industry Co.,Ltd

www.screenmesh-cloth.com

sales@screenmesh-cloth.com bob.yimesh@gmail.com

Call us: +86 311 80815968