



Hebei Gezi Filtration Industry Co., Ltd

Composition	P84/Glass fiber/PTFE	
Weight (g/m ²)	800	
Thickness (mm)	2.5	
Air permeability (L/m ² /s)	8-15	
Tensile strength (N/5×20cm)	Warp	3000
	Weft	3100
Tensile elongation (%)	Warp	<10
	Weft	<15
Broken strength (Mpa/min)	3.85	
Working temperature(°C)	250	
Short time working temperature(°C)	270	
Anti-acid	Excellent	
Anti-alkali	Excellent	
Anti-abrasion	Excellent	
The stability of water solution	Medial	
Finishing treatment	PTFE treatment	

Copyright ©1997-2014 Hebei Gezi Filtration Industry Co.,Ltd

www.screenmesh-cloth.com

sales@screenmesh-cloth.com bob.yimesh@gmail.com

Call us: +86 311 80815968